

# Technical data sheet

Date: January 18, 2022

# SteriKraft S Cal

WHITE MG KRAFT PAPER

Production Unit: Skärblacka

#### End uses

Sterikraft S Cal is a bleached wet strength paper with excellent bacterial barrier properties suitable as a base paper for PVA, Cold Seal or Heat Seal coatings. Sterikraft S Cal is calendered for a smoother surface, giving an enhanced coating efficiency.

# Grammages

60 gsm

#### Materials

Sterikraft S Cal is produced from pure bleached pulp and consists entirely of primary fibers. The long and strong fibres, from the forests of the Nordic region, give the paper its inherent strength.

# **Sterilization Method**

The packed product can be sterilized by treatment with ETO or irradiation sterilization.

#### Approvals

Sterikraft S Cal is produced in compliance with ISO11607-1 and EN868-6.

# Certification

Sterikraft S Cal is produced at Billerud Skärblacka, which is certified in accordance with ISO 9001, ISO 14001, ISO 50001 and FSSC 22000.

Property	Unit			Method
Grammage	g/m²		60	ISO 536
Tensile strength	kN/m	MD CD	6.7 3.9	ISO 1924-3
Tensile strength, wet	kN/m	MD	1.2	ISO 3781
Tearing resistance	mN	MD CD	450 510	ISO 1974
Bursting strength	kPa		280	ISO 2758
Air resistance	s		30	ISO 5636-5
Porosity (Bendtsen)*	ml/min		400	ISO 5636-5*
Cobb 60s	g/m²	MG	19	ISO 535
Roughness (Bendtsen)	ml/min	MG	60	ISO 8791-2
pH hot water extract			6	ISO 6588-2

\*Calculated from Gurley measurements

MD = Machine Direction CD = Cross Direction MG = MG-side/RS = Reverse side Test climate: 50% RH, 23C

The table shows typical values

General www.billerud.com