

## Pure DecorX™ LINER

Production Unit: Gruvön Mill, KM7

### Product Description

The light coated Pure DecorX™ kraftliner is a preferred material for high quality post-print and pre-print. High strength ensures light, strong packages with minimised washboarding. Pure DecorX™ is produced from 100% virgin fibres.

### Grammages

145, 160, 175 g/m<sup>2</sup>

### Approvals

Pure DecorX™ is produced in compliance with FDA and BfR packaging norms.

### Certifications

Gruvön Mill is certified in accordance with ISO 9001, ISO 14001 and FSSC 22000.

Property	Unit					Method
Grammage	g/m <sup>2</sup>		145	160	175	ISO 536
Thickness	µm		165	180	195	ISO 534
Scott Bond	J/m <sup>2</sup>		350	350	350	TAPPI T569
Burst strength	kPa		620	700	750	ISO 2758
SCT	CD	kN/m	3,2	3,6	4,0	ISO 9895
Tensile Stiffness	MD	kN/m	1300	1400	1500	ISO 1924
	CD	kN/m	500	600	650	
Roughness PPS-10	PS	µm	1,8	1,9	2,0	ISO 8791-4
Gloss	PS	%	35	35	35	ISO 8254-1
Brightness	PS	%	80	80	80	ISO 2470
Whiteness D65	PS	%	81	81	81	ISO 11475
Cobb	PS	g/m <sup>2</sup>	28	28	28	ISO 535
	RS	g/m <sup>2</sup>	40	40	40	
Moisture		%	7,0	7,0	7,0	ISO 287

MD = Machine Direction

CD = Cross Direction

Test climate: 50% RH, 23°C

Rev. 202012

The table shows typical data for a range of grammages.