



SteriKraft PeelCoat S

WHITE MG KRAFT PAPER

Production Unit: Beetham

End uses

SteriKraft PeelCoat S is a pure MG white Kraft medical paper for cold seal coating applications.

SteriKraft PeelCoat S is designed to offer good holdout and a high surface strength.

SteriKraft PeelCoat S is suitable where peel-ability is required in both directions MD/CD.

Sterilisation

SteriKraft PeelCoat S is suitable for sterilisation by ethylene oxide gas and gamma irradiation.

Grammage

60 gsm

Materials

SteriKraft PeelCoat S is produced from pure, white Kraft pulp consisting entirely of primary virgin fibre

Approvals

SteriKraft PeelCoat S is produced in compliance with ISO 11607-1, EN 868-3

Certification

Beetham mill is certified in accordance with ISO 9001, ISO 14001 and BS OHSAS

Property	Unit				Method
Grammage	g/m ²		60		On Line QCS
Tensile strength	N/15mm kN/m*	MD CD	110 60	7.3* 4.0*	ISO 1924-3
Wet Tensile strength	N/15mm kN/m*	MD CD	15 9	1.0* 0.6*	ISO 3781
Tear strength	mN	MD CD	430 500		ISO 1974
Burst strength	kPa		350		ISO 2758
Wet burst strength	kPa		60		ISO 3689
Porosity Bendtsen (mean)	ml/min		400		ISO 5636-3
Pore Size	µm		12		EN 868
Water absorbance Cobb 60s	g/m ²	MG	19		ISO 535
pH Aqueous hot extract	pH		7		ISO 6588
Roughness	ml/min	MG RS	100 300		ISO 8791-2
Water repellency	S	MG	25		EN 868

MD = Machine Direction CD = Cross Direction MG = MG side RS = Reverse Side Test climate: 50% RH, 23C Issue: 1 Rev: 0 2016-06

This table shows typical values.

* indicates derived value, for information only.