



SupaDrape

CREPED MG REINFORCED KRAFT PAPER

Production Unit: Beetham

End uses

BillerudKorsnäs SupaDrape is a non-woven product, it is ideal for use as a surgical drape.

SupaDrape is a high performance sterilisation material suitable for inner and outer wrapping of medium to large trays & packs.

It offers a combination of high strength, good barrier & softness in conjunction with high resistance to water & low surface tension fluids.

Suitable for sterilisation by steam or ETO

Grammage

60 g/m²

Available in Green (483) & Blue (484).

Materials

SupaDrape is produced from a blend of pure, white primary Kraft pulp and synthetic fibres.

Approvals

SupaDrape is produced in compliance with ISO 11607-1, EN868-2

Certification

Beetham mill is certified in accordance with ISO 9001, ISO 14001 and BS OHSAS 18001

Property	Unit				Method
Grammage	g/m ²		60		ISO 538
Tensile strength	N/15mm kN/m *	MD CD	30 20	2.0* 1.3*	ISO 1924-3
Wet Tensile strength	N/15mm kN/m *	MD CD	20 15	1.3* 1.0*	ISO 3781
Tear strength	mN	MD CD	1050 1330		ISO 1974
Burst strength	kPa		170		ISO 2758
Wet burst strength	kPa		100		ISO 3689
Elongation	%	MD CD	10.0 8.0		ISO 1924-3
pH Aqueous hot extract	pH		6.5		ISO 6588
Water repellency	s	MG RS	30 30		EN 868
IPA repellency	s	MG	8		EN 868
Drape	cm	MD CD	10.5 13.0		EN 868

MD = Machine Direction CD = Cross Direction MG = MG side RS = Reverse Side Test climate: 50% RH, 23C Issue: 5 Rev:3 2009-12

The table shows typical values.

* indicates derived value, for information only.